



BUILDING PRODUCTS OF CANADA CORP.

TECHNICAL DATA SHEET

NATURAL WOOD FIBRE PANELS

(STANDARD CAN/ULC S706)

NATURAL PANEL AND SOUND DEADENING BOARD 7/16"

DESCRIPTION:

The **Natural Panel 7/16"** or **Sound Deadening Board 7/16"** is rigid panel produced from non-toxic organic material and natural wood fibres that are wax impregnated. The wax impregnation resists water penetration into the board. The density and rigidity of the board provide excellent noise control properties.

USES:

The panels are used on the interior of frame construction and on interior walls, where it contributes to the absorption of sound transmitted from the exterior or other rooms.

STORAGE:

The wood fibre panels must be stored 100 mm (4") above ground level and adequately protected from the elements with tarpaulins.

SIZES AND PACKAGING

SKU	Dimensions	Panels/Bundle	Coverage/bundle
BSNAT8	1219 mm x 2438 mm 48" x 96"	110	327.2 m ² (3520 ft ²)
BSNAT9	1219 mm x 2743 mm 48" x 108"	110	368.1 m ² (3960 ft ²)

CHARACTERISTICS	UNITS		RESULTS BP		REQUIREMENTS		TEST METHOD
	METRIC	IMPERIAL	METRIC	IMPERIAL	METRIC	IMPERIAL	
Nominal Thickness 11.0 mm (0.44")	%	%	Pass	Pass	+/-10%	+/-10%	ASTM C209
Thermal Resistance min. 25.4 mm (1")	RSI	R	Pass	Pass	0.41	2.43	ASTM C518
Transverse Load at Rupture, min avg.	N	lbf	Pass	Pass	45	10.1	ASTM C209
Tensile Strength Parallel to Surface, min avg.	kPa	lb/in ²	Pass	Pass	700	101.5	ASTM C209
Compression Strength at 10% deformation, min avg.	kPa	lb/in ²	Pass	Pass	100	14.5	ASTM C165
Linear Moisture Expansion, max.	%	%	Pass	Pass	0.5	0.5	ASTM D1037
Water Absorption max.2 hours	%	%	Pass	Pass	10	10	ASTM C209
Surface Burning Characteristic, max.	FSR	FSR	Pass	Pass	220	220	ULC S102

APPLICABLE STANDARDS

CAN/ULC S706-09, Type I Class 3

Using BP natural panels or sound deadening boards can contribute to qualifying for green building certification programs like LEED® audited by Vertima

* Building Products of Canada Corp. has all required documents regarding LEED® and can provide information in a certified project.